

RADIANZ®

The information contained herein is provided by Samsung SDI and its subsidiaries and affiliates (collectively referred to as "Samsung") for information purposes only and should be used by individuals with technical experience and knowledge in the area. Samsung does not make any representation or warranties of the usefulness or expected result of the information, and does not assume any responsibility whatsoever related to the use of the information. Exclusion of the implied warranties may not apply in certain jurisdictions.

Test Item	TYPICAL RESULT	TEST PROCEDURE	REMARKS
Geometric properties	No defect	EN 14617-16	Surface quality
Flexural Strength	58.7Mpa	EN 14617-2	
Density	2.359g/cm ³	EN 14617-1	
Water Absorption	0.05%	EN 14617-1	
Compressive Strength	235Mpa	EN 14617-15	
Chemical Resistance	C4	EN 14617-10	
Linear Thermal Expansion	2.7x10 ⁻⁵ °C	EN 14617-11	
Dimension Stability	Class A	EN 14617-12	
Impact Resistance	16J	EN 14617-9	T: 30mm, H: 1.68m
Freeze-Thaw Resistance	0.98%	EN 14617-5	
Thermal shock	2.90%	EN 14617-6	
Abrasion Resistance	21.4mm	EN 14617-4	
Slip Resistance	Wet: 19	EN 14231	
Electrical Resistance	2.24x10 ¹⁰ Ω	EN 14617-13	
Heat Conductivity	2.12W/mk	EN 12664	
Fire Classification	A2fl S1	EN 13501-1	Flooring materials

This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of Samsung products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.

Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, Samsung SDI assumes no responsibility for its suitability or accuracy or the use of such information for products other than Samsung Staron® solid surfaces & Radianz® quartz surfaces.