TECHNICAL BULLETIN

Flammability



1. Test method

• ASTM E 84

Surface Building Characteristics of Building Materials

Sample preparation and conditioning:

Three pieces of sample were placed into the fire chamber end to end supported on screen and rods, to form a 21 inches wide X 24 feet long for testing, than was covered with inorganic cement boards to protect the chamber lid.

Test procedure:

The tunnel was thoroughly pre-heated by burning natural gas. When the brick temperature, sensed by a floor thermocouple, had reached the prescribed 105° Fahrenheit +/-5° Fahrenheit level, the sample was inserted in the tunnel and test conducted in accordance with the standard ASTM E84-09 procedure.

The operation of the tunnel was checked by performing a 10-minute rest with inorganic board on the day of the test.

Rating:

The National Fire Protection Association Life Safety Code 101, Section 6-5.3, "Interior Wall and Ceilling Finish Classification", has a means of classifying materials with respect to Flame Spread and Smoke Developed when tested in accordance with NFPA 255, "Method of Test of Surface Burning Characteristics of Building Materials" (ASTM E84).

FLAME SPREAD	SMOKE DEVELOPED	RATING
0 – 25	0 - 450	Class A
26 - 75	0 - 450	Class B
76 - 200	0 - 450	Class C

2. Test result

- Flame Spread : 10
- Smoke Developed : 180
- Rating : Class A

This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of Samsung products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.

Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, Samsung SDI assumes no responsibility for its suitability or accuracy or the use of such information for products other than Samsung Staron® solid surfaces & Radianz® quartz surfaces.

